

Technical Data LOOSE-LAY COLLECTION



LOOSE-LAY/30

LOOSE-LAY/55

Covering type in accordance with EN ISO 10582	Heterogeneous Plankwood/Tiles, type 1	
Number of colours	14 Planken / 6 Fliesen	
Pack. Unit/Pallet	914x183 mm: 1.67 m ² /125.25 m ² 457x457 mm: 1.67 m ² /120.24 m ² 610x305 mm: 1.67 m ² /120.24 m ² 600x600 mm: 1.80 m ² /129.60 m ²	
Performance classification EN ISO 10582 / ISO 10874	23, 31	23, 33, 42
Total thickness ISO 24346	4.2 mm	
Wear layer thickness ISO 24340	0.3 mm	0.55 mm
Surface treatment	yes/PU	
Bevelled edges	no	yes
Total weight ISO 23997	7.46 kg/m ²	7.23 kg/m ²
Residual indentation ISO 24343-1	≤ 0.1 mm*	
Dimensional stability ISO 23999	≤ 0.15 %*	
Castor chair suitability ISO 4918	suitable for castor chairs in acc. with EN 12529, type W	
Underfloor heating EN 1264-2	suitable (up to 28°C)	
Behaviour to fire EN 13501-1	Bfl-s1	
Resistance to thermal conductivity ISO 8302 / EN 12667	0.02 m ² K/W	
Electrical propensity when walked upon EN 1815	< 2 kV	
Impact sound improvement ISO 10140-3	6 db	
Colour fastness to artificial light ISO 105-B02/2	≥ 7	
Electrostatic characteristics EN 1081	> 10 ¹²	
Chemical resistance ISO 26987	conforms**	
Slip resistance	R9 to R10 (depending on design)	
Maintenance/Cleaning recommendation	Dr. Schutz	

* Averaged value

(Date: 05/02/2018)

** Vis-à-vis the short-term effects of normal, domestic agents.

Please also note the installation and cleaning and care instructions.

